



PureCal™ 12-40

Feed Grade Calcium Carbonate

Description:

Ground and screen granular grades produced from high calcium limestone from underground mines. "Calcite", "crushed marble", and "ground limestone" are synonymous with ground natural "calcium carbonate".

TYPICAL PARTICLE DISTRIBUTION

US SCREEN	% PASSING
10	99.69
12	98.57
16	75.35
20	28.09
30	3.88
50	<1

CHEMICAL SPECIFICATIONS

	TYPICAL
Calcium (Ca)	39.50%
Calcium Carbonate (CaCO ₃)	99.30%

TYPICAL PHYSICAL CHARACTERISTICS

Bulk Density	90lbs/ft ³
Moisture	< 0.05%
Appearance	light gray -gray
pH (ASTM - D1208)	9.3

IMPURITIES, TYPICAL

Magnesium	(Mg)	0.20%
Silica	(SiO ₂)	0.30%
Iron	(Fe)	0.0456%
Aluminum	(Al)	0.0010%
Arsenic	(As)	< 0.5 ppm
Cadmium	(Cd)	< 0.8 ppm
Lead	(Pb)	< 3.2 ppm
Mercury	(Hg)	< 0.1 ppm

Cerne Calcium Company
 2123 200th Street
 Fort Dodge, IA 50501

Ordering Information:
 515.223.8844
 orders@cernecalcium.com



Cerne Calcium Company (CCC) does not intend or represent that this information or the products to which it relates be used in any manner which would or could infringe patent rights of others. Although we believe the sources of this information to be reliable, CCC disclaims any responsibility or liability for results of using this information since conditions of use are beyond our control.